bosfa

Deep Cycle SLA Battery

DC SERIES

DC (Deep cycle) Series batteries are designed for deep discharge application, with special chemical formula for plates active paste material, slightly stronger electrolyte and low temperature design, which can withstand repeated deep cyclic application, such as Solar Energy System, Golf Trolley, Electric

VRLA Battery

Application

- Solar Energy System
- Golf Cars and Buggies
- Electric Powered Vehicles
- Wheel Chairs

- Power Tools
- Electric Powered Toys
- Control System
- Vacuum Cleaners
- Medical Equipments

General Features


- Sealed and maintenance free operation.
- Non-Spillable construction design.
- ABS containers and covers(UL94HB, UL94V-0) optional.
- Safety valve installation for explosion proof.
- High quality and high reliability.
- Exceptional deep discharge recovery performance.
- Low self discharge characteristic.
- Flexibility design for multiple install positions.

Construction


•	Componer	nt	.Raw material
•	Positive		Lead dioxide
•	Negative		.Lead
•	Container		.ABS
•	Cover		.ABS

- SealantEpoxy Resin
- Safety valveEPDR • TerminalCopper
- SeparatorFibre glass
- ElectrolyteSulfuric acid





Terminal Dimensions






Battery Model	DC 12-7.5						
Designed Cycle Life	> 350 cycles @ -0.5CA to 9.6V						
Canacity/2E°C)	20HR(0.375A,1.75V)	10HR(7.12A,1.75V)	5HR(1.276A,1.75V)	1HR(4.87A,1.75V)			
Capacity(25°C)	7.5AH	7.12AH	6.38AH	4.87AH			
Dharandana	Length	Width	Height	Total Height			
Dimensions	151mm(5.94inch)	65mm(2.56inch)	95mm(3.74inch)	101mm(3.98inch)			
Approx. Weight	1.74Kg (3.84 lbs)						
Internal Resistance	Full charged at 25°C: 0.02 Ohm						
Self Discharge	3% of capacity declined per month at (25°C)						
Capacity Affected	40°C	25°C	0°C	-15°C			
by Temp.(20HR)	102%	100%	85%	65%			
Chargo Valtago(2E°C)	Cycle	e use	Float use				
Charge Voltage(25°C)	14.4-15V(-30mV/ °C)	, max. Current: 2.25A	13.6-13.8V(-20mV/ °C)				

VRLA Battery

Deep Cycle SLA Battery



Constant current discharge ratings-amperes at 25°C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	3HR	5HR	10HR	20HR
1.60V	41.8	26.0	19.6	12.0	6.09	2.67	1.63	0.89	0.48
1.67V	39.2	24.7	18.9	11.4	6.01	2.57	1.60	0.88	0.46
1.70V	35.9	23.8	18.4	10.4	5.83	2.40	1.57	0.88	0.46
1.75V	35.2	23.0	17.8	9.88	5.55	2.32	1.53	0.87	0.44
1.80V	31.5	22.0	16.2	9.15	5.20	2.23	1.44	0.86	0.43
1.85V	27.8	20.9	14.6	8.42	4.85	2.15	1.35	0.85	0.42

Constant power discharge ratings-watts at 25°C

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	3HR	5HR	10HR	20HR
1.60V	73.3	46.9	35.8	21.5	13.7	4.74	2.76	1.83	0.96
1.67V	70.7	45.8	35.4	21.1	13.6	4.59	2.75	1.82	0.93
1.70V	66.6	45.3	35.1	19.8	13.4	4.39	2.71	1.81	0.91
1.75V	67.0	45.2	34.8	19.2	13.1	4.29	2.69	1.78	0.89
1.80V	61.3	44.5	32.2	18.3	12.4	4.16	2.61	1.76	0.87
1.85V	55.6	42.2	29.2	17.1	11.7	4.03	2.52	1.74	0.83







COPYRIGHT BOSFA INDUSTRIAL BATTERY CO.,LTD.